

- ▶ NBR 1845 is essentially an acrylonitrile (17-20%) and 1,3-butadiene copolymer obtained by emulsion polymerization method with the use of fatty acid soaps as emulsifier in accordance with the ecologically clean technology. Low content of acrylonitrile, good frost-resistance, satisfactory oil resistance.
- ▶ Product characteristics: appearance – bales from light-yellow to pink color; weight of a bale  $30 \pm 0,5$  kg;
- ▶ Shelf life is 1 year since the date of manufacture. Storage conditions: at the temperature not higher than  $30\text{ }^{\circ}\text{C}$ , in place protected from direct sunlight and atmospheric precipitation.
- ▶ Package: plywood 1,26 mt or plastic container 0,54 mt.

<i>Parameter</i>	<i>NBR 1845</i>	<i>Test method</i>
Mooney viscosity MML 1+4 (100 °C)	42-48	ASTM D 1646
Volatile matter content, wt %	$\leq 0,8$	ASTM D 5668
Ash content, wt %	$\leq 0,5$	ASTM D 5667
Acrylonitrile content, wt %	17-20	method of supplier
<i>ASTM D 3187 (method A), 145 °C × 50 min</i>		
Tensile stress at 300 % elongation, MPa	$\geq 6,4$	ASTM D412
Tensile strength, MPa	$\geq 16,7$	ASTM D412
Ultimate elongation, %	$\geq 400$	ASTM D412
<i>Curing characteristics of rubber compound</i> <i>Rheometer MDR 2000, measurement conditions: 160 °C, deformation of 0.5°, MH at 30 min</i>		
Minimum torque (ML), dNm	1,0-2,2	ASTM D 5289
Maximum torque (MH), dNm	9,6-13,0	ASTM D 5289
Scorching time (ts1), min	2,3-5,5	ASTM D 5289
Time to 50% of full cure (t 50), min	3,4-6,4	ASTM D 5289
Time to 90% of full cure (t 90), min	7,2-10,8	ASTM D 5289

**These figures are only intended as a guide and should not be used in preparing specifications.**