

BR-1203 Ti

Synthetic polybutadiene rubber

Synthetic cis-butadiene rubber BR-1203 Ti is the polymerization product of butadiene in solution; in the presence of titanium catalyst; 1,4-cis – at least 90%. The polymer is stabilized with non-staining antioxidant and contains no nitrosamines or substances that may be a source of nitrosamines.

Appearance: bale from light to dark beige color; weight of a bale — (30 ± 1) kg

Package: PE wrapping film (Vicat softening point ≤ 95 °C); metal and plywood containers (1.26 MT) or cardboard 0,54 MT or plastic container 0,54 MT

Shelf life: 2 (two) years from the date of manufacture
Storage conditions: at the temperature not higher than 30 °C, in place protected from direct sunlight and atmospheric precipitation

Parameters	BR-1203 Ti grade B	Test method
Mooney viscosity UML ₁₊₄ (100 °C), UM	45 ± 4	ASTM D 1646
Volatile matter, % wt	≤0,8	ASTM D 5668
Ash, % wt	≤0,3	ASTM D 5667

Stress-strain properties in standard recipe on ASTM D 3189, 145 °C × 35 min.

Tensile stress at 300 % elongation, MPa	≥8,5	
Tensile strength, MPa	≥11,0	ASTM D 412
Ultimate elongation, %	≥360	

Curing characteristics of rubber compound: Rheometer MDR 2000, measurement conditions: 160 °C, deformation of 0.5°, MH at 30 min.

Minimum torque (ML), dNm	2,7–3,7	
Maximum torque (MH), dNm	16,0–20,0	
Scorch time (ts'1), min.	1,8–3,2	ASTM D 5289
Time to 50 % of full cure (t'50), min.	4,5–8,0	
Time to 90 % of full cure (t'90), min.	8,0–12,0	

Technical support service: techservice@sibur.ru

Issue: **16-March-2020**

MOSCOW

16/1 Krzhizhanovskogo St., Moscow,
117218
Phone: +7 (495) 777-55-00; +7 (495)
780-55-00
E-mail: info@sibur.ru

VIENNA

SIBUR International Gesellschaft m.b.H.
Prinz Eugen-Straße 8-10 1040 Vienna, Austria
tel.: +43 1 370 8000
e-mail: info@sibur-int.com
www.sibur-int.com

ISTANBUL

SIBUR International Trading (Istanbul)
Business Park, B1 Blok, Kat.9, No.318,
Yeşilköy, Bakırköy, Istanbul, Turkey
tel.: +90 (212) 465 2321
e-mail: info@sibur-int.com
www.sibur-int.com

SHANGHAI

SIBUR International Trading (Shanghai) Co., Ltd
Rm.74T71, SWFC Century Ave.100
Pudong New Area, Shanghai
tel.: +86 (021) 2206 5066
e-mail: infoChina@sibur-int.com
www.sibur-int.cn