

## PRODUCT DESCRIPTION

PE HD10530 LB is a high molecular weight hexene copolymer for Medium Blow Molding applications. The grade combines high impact resistance, good rigidity and very high environmental stress crack resistance (ESCR).

## TYPICAL APPLICATIONS

PE HD10530 LB is recommended for Blow Molded articles such as jerrycans, high performance containers up to 60 liters for the packaging of aggressive products.

Properties	Conditions	Method	Typical values*	Units
<b>Rheology</b>				
Melt Flow Rate	190 °C/21.6 kg	ISO 1133-1	10	g/10 min
<b>Physical</b>				
Density		ISO 1183	0.953	g/cm <sup>3</sup>
<b>Mechanical</b>				
Tensile Stress at Yield		ISO 527-1	26	MPa
Elongation at Break		ISO 527-1	400	%
Flexural Modulus		ISO 178	1000	MPa
Charpy Notched Impact Strength	23 °C	ISO 179	12	kJ/m <sup>2</sup>
Notched Izod Impact Strength	-20 °C	ASTM D256	19	kJ/m <sup>2</sup>
BTT Stress Crack Resistance	F50, 100 %	ASTM D1693	>1000	hours

\*The values given are typical values measured on the product. These values should not be considered as specification.

### REACH Statement

Polymers are exempt of REACH registration. However, their raw materials which mean monomers and relevant additives have been registered.

**PJSC «Sibur Holding» (and its subsidiaries)** is committed to fully respect REACH legislation and to use only REACH compliant raw materials.

## Safety

See MSDS

## Contact

### PJSC «Sibur Holding»

Basic Polymers Division  
3-16, Krzhizhanovskogo St.  
117997, Moscow, Russian Federation  
Tel.: ++7 495 7775500  
E-mail: [servicedbp@sibur.ru](mailto:servicedbp@sibur.ru)

### European Sales Office

Sibur International GmbH  
Prinz Eugen Straße 8-10  
1040, Vienna, Austria  
Tel.: ++43 1 370 8000  
E-mail: [polyolefins@sibur-int.com](mailto:polyolefins@sibur-int.com)

### Turkey Sales Office

SIBUR International Trading Istanbul  
EGS Business Park, B1 Blok, Kat.9, No.318 Yeşilköy,  
Bakırköy  
Istanbul, Turkey  
Tel: ++90 212 465 2321  
E-mail: [polyolefins@sibur-int.com](mailto:polyolefins@sibur-int.com)

### Chinese Sales Office

SIBUR International Trading (Shanghai)Co., Ltd  
Rm.62T70, SWFC, Century Ave.100 Pudong New  
Area, 200120, Shanghai, China  
Tel: ++86 021 2206 5066 ext 215  
E-mail: [serviceCN@sibur-int.com](mailto:serviceCN@sibur-int.com)

**The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications. To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information. PJSC «Sibur Holding» (and its subsidiaries) makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.**

**It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of any PJSC «Sibur Holding» (and its subsidiaries) product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.**