



Styrene Monomer

TECHNICAL CHARACTERISTICS

Description of index	Standard
	Superior quality
General appearance	Transparent homogeneous liquid w/o undissolved moisture and mechanical admixture
Fraction of total mass of styrene, %, minimum	99.8
Fraction of total mass of phenylacetylene, %, maximum	0.01
Fraction of total mass of divinyl benzene, %, maximum	0.0005
Fraction of total mass of carbonyl compounds in conversion into benzaldehyde, %, maximum	0.01
Fraction of total mass of peroxide compounds in conversion into active oxygen, %, maximum	0.0005
Fraction of total mass of polymer, %, maximum	0.001
Color index by platinum-cobalt scale, Khazen's units, maximum	10
Fraction of total mass of stabilizer of para-tert-butyl pyrocatechol, %	0.0005-0.001

Packing: in bulk

Origin: Russia

COMPANY COMMUNICATION:

Tel.: +43 1 370 8000-0
Fax.: +43 1 370 8000-20
<http://www.sibur-int.com/>

COMPANY ADDRESS:

Nussdorfer Platz 8
1190 Vienna
AUSTRIA

COMPANY DETAILS:

Place of Jurisdiction: Vienna
Commercial Register Nr.: FN 229446X
VAT Registration No. ATU 56388233