


Modified copolymer corona treated skin layer
White opaque oriented polypropylene tie layer
White Pearl cavitated core layer of oriented polypropylene
Oriented polypropylene tie layer



Glossy non heat sealable, non corona treated skin layer with standard coefficient of friction

DESCRIPTION:

White Pearl microporous BOPP film
for fully wrapped labeling of bottles
for cold and hot melt glue application while labeling
with very high yield good gloss and good ink adhesion

Properties		Methods			Unit	LOBC					
Thickness, ± 5%		BIAXPLEN			mkm	35	38	47			
Density *								g/cm ³	0,55		
Weight, ± 5%								g/m ²	19,25	20,90	25,85
Yield, ± 5%								m ² /kg	51,95	47,85	38,68
Tensile strength, not less	MD	GOST 14236	ISO 527	ASTM D882	N/mm ² , MPa	60					
	TD					120					
Elongation at break, not more	MD							%	180		
	TD								60		
Coefficient of friction, kinetic	UT/UT	GOST 27492	ISO 8295	ASTM D 1894	---	0,3	- 0,1	+ 0,1			
Thermal shrinkage at 120°C, 5 min, not more	MD	GOST 18616	ISO 11501	ASTM D1204	%	4					
	TD					2					
Light transmission, not more		GOST 15875	ISO 14782	ASTM D 1003	%	30	25				
Gloss at 45°, not less	T	BIAXPLEN	ISO 2813	ASTM D 2457	%	80					
Treatment level, not less	T	BIAXPLEN	ISO 8296	ASTM D 2578	Dyne/cm, mN/m	38					

MD - Machine, longitudinal direction;
TD - Transverse direction

T - treated side of the film;
UT - untreated side of the film;

* Typical value
GOST - Russian Federation standards.

MAIN PROPERTIES:

- Very low density and very high yield;
- high adhesion of solvent based inks: flexo and rotogravure for printing;
- both side glossy film;
- good opacity and whiteness;
- contains mineral fillers such as calcium carbonate and titanium dioxide;
- contains slip, antistatic and antiblock additives;
- low coefficient of friction, stable in time;
- without coating or primer.

APPLICATION:

- High quality solvent based rotogravure and flexographic printing;
- for production of fully wrapped labels for bottles;
- for labeling with cold and hot melt glue ;

Attention! Information specified in this document is for reference only; it contains averaged technical characteristics of BIAXPLEN LTD products based on results of laboratory tests performed in BIAXPLEN LTD standard operation conditions. BIAXPLEN LTD gives no representations and/or warranties and is expressly relived from any liability for infringement of any third parties' intellectual property rights arising from processing of BIAXPLEN LTD products.

Testing of BIAXPLEN LTD products in order to determine their suitability in terms of meeting specific objectives of a person intending to purchase BIAXPLEN LTD products is the sole responsibility of such a person who shall be responsible for any consequences related to processing and use of BIAXPLEN LTD products.

This document does not constitute a quotation and its provision to any person shall not create any rights and duties on the part of BIAXPLEN LTD.