


High glossy aluminum layer  
Modified layer for aluminum adhesion  
Oriented polypropylene tie layer  
White Pearl cavitated core layer of oriented polypropylene  
Oriented polypropylene tie layer  
Glossy non heat sealable, non treated skin layer with standard coefficient of friction



**DESCRIPTION:**

White pearl metallized microporous BOPP film  
for labeling of bottles, for cold and  
hot melt glue application while labeling.

Properties		Methods			Unit	LOHM.M		
Thickness, ± 5%		BIAXPLEN			mkm	35	38	
Density *					g/cm <sup>3</sup>		0,71	
Weight, ± 5%					g/m <sup>2</sup>		24,85	26,98
Yield, ± 5%					m <sup>2</sup> /kg		40,24	37,06
Tensile strength, not less	MD	GOST 14236	ISO 527	ASTM D882	N/mm <sup>2</sup> , MPa	90		
	TD					180		
Elongation at break, not more	MD					200		
	TD					70		
Coefficient of friction, kinetic	UT / UT	GOST 27492	ISO 8295	ASTM D 1894	---	0,3	+0,15 -0,15	
Thermal shrinkage at 120°C, 5 min, not more	MD	GOST 18616	ISO 11501	ASTM D1204	%	4		
	TD					2		
Optical density, not less		BIAXPLEN			O.D.	1,8		
Treatment level, not less**	T	BIAXPLEN	ISO 8296	ASTM D2578	Dyne/cm, mN/m	36		

MD - Machine, longitudinal direction;  
TD - Transverse direction

T - metallized side;  
UT - white pearl, non treated side;

\* Typical value  
GOST - Russian Federation standards.

\*\* Guaranteed shelf life of the activation of the metallized side is 15 days from the date of manufacture indicated on roll label;

**MAIN PROPERTIES:**

- Very smooth surface and high gloss metallized side;
- excellent adhesion of the aluminum layer;
- lower density, high opacity and good whiteness;
- permanent coefficient of friction and good mechanical properties;
- contains an organic dye pearl and non-migratory slip additives;
- intended for contact with food;
- without coating and primer.

**APPLICATION:**

- High quality solvent based rotogravure and flexographic direct printing;
- for production of fully wrapped labels for bottles;
- for labeling with cold and hot melt glue;

Attention! Information specified in this document is for reference only; it contains averaged technical characteristics of BIAXPLEN LTD products based on results of laboratory tests performed in BIAXPLEN LTD standard operation conditions. BIAXPLEN LTD gives no representations and/or warranties and is expressly relieved from any liability for infringement of any third parties' intellectual property rights arising from processing of BIAXPLEN LTD products. Testing of BIAXPLEN LTD products in order to determine their suitability in terms of meeting specific objectives of a person intending to purchase BIAXPLEN LTD products is the sole responsibility of such a person who shall be responsible for any consequences related to processing and use of BIAXPLEN LTD products.

This document does not constitute a quotation and its provision to any person shall not create any rights and duties on the part of BIAXPLEN LTD.